Polypropylene Aramco PP HP30G

Product Description

Aramco PP HP30G is a homopolymer polypropylene resin and is typically used for yarn extrusion characterized by ease of processing and low heat shrinkage. Yarn made from this resin typically exhibits excellent mechanical properties. This product is also typically used for thermoforming application.

Typical Applications

Woven sacks, woven cloths, monofilament, binding tape, thermoforming.

This product is not intended for use in medical and pharmaceutical applications.

Physical Properties	Unit	Test Method	Value ⁽¹⁾	
Melt Flow Index (190°C/2.16kg)	g/10min	ASTM D1238	3.0	
Density	g/cm³	ASTM D792 Method A	0.9	
Mechanical Properties ⁽²⁾			1 1 4 6	
Tensile Strength at Yield	MPa	ASTM D638	34	
Tensile Elongation at Yield	%	ASTM D638	9	
Tensile Strength at Break	MPa	ASTM D638	19	
Tensile Elongation at Break	% 61101	ASTM D638	165	-, -
Flexural Modulus	MPa	ASTM D790	1300	
Flexural Strength	MPa	ASTM D790	35	
Izod Impact, Notched 23 °C	kJ/m²	ASTM D256	3.0	
Hardness Rockwell		ASTM D785	98	
Thermal Properties ⁽²⁾				
Vicat Softening Temperature @10N	°C	ASTM D1525	152	

⁽¹⁾ Typical values only, not to be construed as specification limits

Processing conditions: Recommended extrusion temperature : 250 °C

Recommended stretching temperature $: 155 \,^{\circ}\text{C}$ Recommended stretching ratio : 4-6

Storage and handling: Aramco PP HP30G should be stored in a dry cool place with adequate ventilation and protected from UV-light at temperature below 50 °C

Food Contact and other Regulations: Aramco PP HP30G resins are suitable for food contact applications. Detailed information is provided in Material Safety Datasheet and for additional specific information, please contact Saudi Aramco Products Trading Company for certificates.

Disclaimer: © Saudi Aramco Products Trading Company. All information supplied by or on behalf Saudi Aramco Products Trading Company in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Saudi Aramco Products Trading Company assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or products. Trading Company for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers and other information.

⁽²⁾ Test specimen preparation method: Pursuant to ASTM D4101